




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁴ : C03B 37/14, G02B 6/42, 6/26	A1	(11) International Publication Number: WO 89/10332 (43) International Publication Date: 2 November 1989 (02.11.89)
<p>(21) International Application Number: PCT/GB89/00455</p> <p>(22) International Filing Date: 28 April 1989 (28.04.89)</p> <p>(30) Priority data: 8810286.8 29 April 1988 (29.04.88) GB</p> <p>(71) Applicant (for all designated States except US): BRITISH TELECOMMUNICATIONS PUBLIC LIMITED COMPANY [GB/GB]; 81 Newgate Street, London EC1A 7AJ (GB).</p> <p>(72) Inventor; and (75) Inventor/Applicant (for US only) : FORRESTER, David, Stewart [GB/GB]; 22A Fonnereau Road, Ipswich, Suffolk IP1 3JP (GB).</p> <p>(74) Agent: GREENWOOD, John, David; British Telecommunications public limited company, Intellectual Property Unit, 151 Gower Street, London WC1E 6BA (GB).</p>		<p>(81) Designated States: AU, JP, US.</p> <p>Published <i>With international search report.</i></p>

(54) Title: CONNECTING OPTICAL WAVEGUIDES



(57) Abstract

A method of splicing optical fibres is described in which at least one of the fibres has a high numerical aperture (NA) and the two fibres have different mode spot sizes. The method comprises fusing the ends of the fibres together with their cores in alignment and heating the fused junction between the fibres so as to cause dopant to migrate out of the core. The heating step is carried out for a time sufficient to achieve a predetermined level of matching between propagation modes in the two fibres.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	ML	Mali
AU	Australia	GA	Gabon	MR	Mauritania
BB	Barbados	GB	United Kingdom	MW	Malawi
BE	Belgium	HU	Hungary	NL	Netherlands
BG	Bulgaria	IT	Italy	NO	Norway
BJ	Benin	JP	Japan	RO	Romania
BR	Brazil	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	LI	Liechtenstein	SN	Senegal
CH	Switzerland	LK	Sri Lanka	SU	Soviet Union
CM	Cameroon	LU	Luxembourg	TD	Chad
DE	Germany, Federal Republic of	MC	Monaco	TG	Togo
DK	Denmark	MG	Madagascar	US	United States of America
FI	Finland				

Connecting Optical Waveguides

The invention relates to methods for connecting optical waveguides, such as optical fibres.

5 A conventional optical waveguide comprises a length of dielectric material having a cross-sectional refractive index profile which is peaked such that optical radiation travelling along the length of material is guided to remain within the material of the waveguide.
10 The material within the peak region is generally known as the core, and the material outside the peak region is generally known as the cladding.

Conventionally, optical waveguides of this type are connected or spliced together by bringing adjacent ends
15 of the waveguides together under force in the presence of an electrical arc which, after the ends have been brought together, is turned off. This causes the fibres to fuse together. In some cases, the fused joint is annealed to improve mechanical strength. It is important to take
20 account of the major splice loss mechanisms which exist in order to minimise losses resulting from the fused connection. In general, these loss mechanisms can be divided into three:

Transverse core offsets - this is caused by the core
25 being non-concentric with the waveguide so that even if the waveguides are accurately aligned, the cores are not.

Core deformation - this is caused by poor alignment of the waveguides before the splice and/or the fact that the adjacent ends of the waveguides are not aligned.

30 Mode field mismatch - the refractive index profile controls the cross-sectional width of an optical field propagating in the waveguide as measured between the $1/e$ intensity levels and is characterised by the "mode spot size".

35

In a typical monomode fibre having a core diameter of about $8\mu\text{m}$, the mode spot size will be in the order of $9\mu\text{m}$. If the mode spots have different shapes (or sizes) in the two waveguides then there will be significant losses at the joint.

If the two waveguides have significantly different mode spot sizes, then the mode mismatch will be the dominant loss mechanism. Various proposals have been made to deal with this. For example, EP-A-0076186 describes a method of heating the ends of the fibres to a temperature of 800°C to 1200°C for a period of 24 to 48 hours to cause migration of dopant in the core in to the cladding since this results in modification of the refractive index of the optical fibre and a corresponding change in the mode spot size. The main disadvantages of this process are the need for a lengthy pre-treatment (1 to 2 days) and the necessity to cleave the fibre in the correct place to match mode sizes.

The effect of fluorine migration from cladding to core on the refractive index profile has been described in "Theory of tapering single-mode optical fibre by controlled core diffusion" by C.P. Botham and "Tapers in single-mode optical fibre by controlled core diffusion" by J.S. Harper, C.P. Botham, and S. Hornung both in Electronics Letters 18th February 1988, vol. 24 No. 4, pages 243 - 246. Both these papers are concerned with a single fibre and the effect on that fibre of a heating process and illustrate typical heating times in the order of 1 hour or more.

In accordance with the present invention, a method of connecting optical waveguides having different refractive index profiles and at least one of the waveguides having a high numerical aperture (NA) comprises fusing the ends of the waveguides together with their cores in alignment and subsequently heating the

fused junction between the waveguides so as to cause dopant to migrate out of the core of the high-NA waveguide, the heating step being carried out for a time sufficient to achieve a predetermined level of matching
5 between the mode spot sizes in the two waveguides.

We have found that in the proposals described above, all of which are concerned with low NA fibres, losses increase rapidly when the fibres are subjected to heat treatment. In contrast, we have found that a post
10 fusion heat treatment is surprisingly effective when at least one of the waveguides has a high-NA. When splicing a high-NA fibre to a standard fibre the differential migration rates in the two fibres produces a quick equalisation of mode spot sizes. When splicing two
15 high-NA fibres together the two cores quickly grow in size together reducing physical mismatch such as transverse core offsets. We have found that highly doped, high-NA fibres have rapid migration of the dopant on heating that leads to a short post splice heat
20 treatment to effect mode spot size matching or transverse core offset reduction. It has been found that by choosing a suitable heating power it is possible to achieve significant mode spot size matching within a comparatively short time, typically in the order of 30
25 seconds. The post heating could be carried out using the same arc as is used to achieve fusion or by some other heating process and in the former case heating power will be determined by suitably choosing the arc current.

In practice the temperature reached during the post
30 heating process will be higher than has hitherto been achieved for example in the known anneal procedures and in EP-A-0076186. Typically, temperatures in the order of 1400°C - 1600°C will be used.

In one example, the variation of propagation loss
35 can be monitored during the fusion and post heating

process in order to determine when the post heating process should be stopped. Alternatively, this monitoring process can be carried out in a preliminary step to determine the appropriate heating time and for
5 subsequent connections, the post heating process can be applied for that predetermined time without real time monitoring being necessary.

Preferably, the heating step is carried out until propagation losses reach a minimum. Alternatively, or
10 additionally, the heating process can be carried out until propagation losses are reduced by at least 1 dB over the loss occurring when the waveguides are butted together but not fused.

The numerical aperture of the high-NA waveguide will
15 generally be at least 0.15 and typically lie in the range 0.15 to 0.3.

The invention is particularly applicable to the connection of a conventional monomode optical fibre to a high-NA fibre. Such high-NA fibres are used in fibre
20 lasers and for coupling optical power out of lasers. The invention is also applicable to the connection of two high-NA fibres.

The apparatus for carrying out the method may be a conventional optical fibre splicing apparatus suitably
25 adjusted in particular to modify the arc duration and arc current from conventional values.

An example of a method in accordance with the invention will now be described with reference to the accompanying drawings, in which:-

30 Figure 1 illustrates the refractive index profile of a high-NA optical fibre before and after splicing;

Figure 2 is a diagram similar to Figure 1 but for a conventional, monomode optical fibre; and,

Figure 3 illustrates the variation in propagation
35 loss with time; and

Figure 4 is a schematic diagram of a high NA fibre spliced to a low NA communications fibre and coupled to a semiconductor laser.

As has been mentioned previously, the invention is particularly suitable for use in splicing high-NA optical fibres. These splices may involve the connection of a high-NA fibre to standard fibre, or the connection of two high-NA fibres. In this example, the connection of a high-NA fibre to a standard fibre will be described.

The numerical aperture (NA) of an optical fibre is given by

$$(n_{co}^2 - n_{cl}^2)^{\frac{1}{2}} \approx (2n_{cl} \times \delta n)^{\frac{1}{2}}$$

where n_{co} is the refractive index of the core,

n_{cl} is the refractive index of the cladding, and

$$\delta n = n_{co} - n_{cl}.$$

High-NA fibres have a large δn typically in the range of 0.02 to 0.008 corresponding to an NA in the range 0.24 to 0.15. In germania doped silica fibres this is achieved by having a large germania concentration in the core region. Figure 1 illustrates with a line 1 the refractive index profile of such a high-NA fibre. This fibre will have a core radius, a , of about 2 microns and a mode radius of about 2 microns.

The refractive index profile of a conventional, monomode fibre to which the high-NA fibre is to be spliced is shown in Figure 2 by a line 2. In this case, δn is about 0.004, a is about 4 microns and the mode radius is about 5 microns. It will be appreciated therefore that there is a significant difference in mode spot size between the two fibres.

After preparing the ends of the fibres in a conventional manner so as to be as flat as possible, the fibres are mounted in a conventional splicing machine and backed off by a small distance to allow an arc to be struck through the space between the fibres. The fibres are then brought together at speed in the presence of the arc which causes the fibres to fuse. In contrast to conventional splicing, the arc is maintained on for a total of 25 to 30 seconds.

The effect of this additional heating after fusion is to cause the dopant in the core of the high-NA fibre to migrate into the cladding of that fibre. This migration will cause changes in the refractive indices of the core and cladding and effectively reduce the value of δn for that fibre. This migration occurs much more quickly in the high-NA fibre than in the standard fibre due to the high concentration of dopant in the core. This high concentration lowers the "softening" temperature of the core (as compared to the cladding, or to the core of the less heavily doped fibre), so that the mobility of the germanium atoms is greatly increased at any given temperature.

Since the mode width in an optical fibre is very strongly dependent upon the value of δn and the core radius, a , especially when a is small, small changes in δn and a , brought about by diffusion of the core dopant, can produce large changes in the mode width.

As can be seen in Figure 1, after heating for about 25 seconds, the refractive index profile has changed significantly to the form shown by the line 3. However, as shown in Figure 2, it will be seen that the refractive index of the conventional or standard fibre has changed very little as shown by the line 4. However, a comparison of these diagrams will indicate that the refractive index profiles 3, 4 are now very similar.

The arc current during the post heating process is chosen so that the temperature of the fibres is raised to their softening point typically in the order of 1400 - 1600°C.

The effect on propagation loss during the process can be seen in Figure 3. Initially, the two fibres are butted together during a period 5. They are then backed off which will inevitably cause an increase in losses, while the arc is struck during a period 6. While the arc

is maintained on the fibres are brought together and fused. In a standard splicing technique, the arc would be turned off at the end of a period 7, about 2 to 3 seconds after the fibres are brought together. In the
5 invention, however, heating is continued by maintaining the arc on and it will be seen that gradually losses continue to decrease until they reach a minimum of about 0.2dB at about 25 seconds after the fibres were brought together in the presence of the arc. Figure 3
10 illustrates the effect on losses at 1.3 microns (line 8) and at 1.5 microns (line 9) and it will be seen that these are very similar.

Although the invention has been described in connection with a highly doped core, it is also
15 applicable to fibres having a highly doped cladding (for example with fluorine or boron dopant) to decrease the refractive index of the cladding or a combination of these.

Referring now to Figure 4, there is shown a high NA fibre 40
20 positioned to couple light from a semiconductor laser 42 and spliced to a low NA communications fibre 42 by the above described method of the present invention. This combination provides a low loss coupling between the laser 42 and the communications fibre 44. This combination
can be supplied as a package, the first 44 being a pig tail for
25 splicing by conventional means to a similar fibre (not shown) of an optical communications system.

30

35

SUBSTITUTE SHEET

CLAIMS

1. A method of connecting optical waveguides having different refractive index profiles and at least one of
5 the waveguides having a high numerical aperture (NA), the method comprising fusing the ends of the waveguides together with their cores in alignment and subsequently heating the fused junction between the waveguides so as to cause dopant to migrate out of the core of the high-NA
10 waveguide, the heating step being carried out for a time sufficient to achieve a predetermined level of matching between the mode spot sizes in the two waveguides.
2. A method according to claim 1, wherein the heating step is carried out for a time not exceeding 30 seconds.
- 15 3. A method according to claim 1 or claim 2, wherein the fused junction is heated to at least 1400°C during the heating step.
4. A method according to any of the preceding claims, wherein the heating step is carried out until propagation
20 losses reach a minimum.
5. A method according to any of the preceding claims, wherein the heating step is carried until propagation losses have been reduced by at least 1dB over the losses occurring when the waveguides are butted together but not
25 fused.
6. A method according to any of the preceding claims, further comprising monitoring the propagation losses during the heating step.
7. A method according to any of the preceding claims,
30 wherein the numerical aperture of the high-NA waveguide is at least 0.15.
8. A method according to claim 7, wherein the numerical aperture of the high-NA waveguide lies in the range 0.15 to 0.3.
- 35 9. A method according to any of the preceding claims, wherein the waveguides comprise optical fibres.

10. A method of connecting optical waveguides substantially as hereinbefore described with reference to the accompanying drawings.

11. A high-NA optical fibre fused end to end with another optical fibre.

12. A combination according to claim 11, wherein the another optical fibre does not have a high numerical aperture.

13. A combination as claimed in claim 12 in which the high NA fibre is optically coupled to an optical source.

14. A combination as claimed in claim 13 in which the optical source is a semiconductor laser.

1/3

Fig.1.




Fig.4.






Fig.2.




3/3



INTERNATIONAL SEARCH REPORT

International Application No PCT/GB 89/00455

I. CLASSIFICATION OF SUBJECT MATTER (if several classification symbols apply, indicate all) ⁶		
According to International Patent Classification (IPC) or to both National Classification and IPC		
IPC ⁴ : C 03 B 37/14, G 02 B 6/42, G 02 B 6/26		
II. FIELDS SEARCHED		
Minimum Documentation Searched ⁷		
Classification System	Classification Symbols	
IPC ⁴	C 03 B 37/14, G 02 B 6/00	
Documentation Searched other than Minimum Documentation to the Extent that such Documents are included in the Fields Searched ⁸		
III. DOCUMENTS CONSIDERED TO BE RELEVANT ⁹		
Category ¹⁰	Citation of Document, ¹¹ with indication, where appropriate, of the relevant passages ¹²	Relevant to Claim No. ¹³
Y	DE, A, 3609407 (PHILIPS) 24 September 1987 see figure 2; column 1, lines 34-68; column 2, lines 1-68; column 3, lines 1-7	1
A	--	2, 3, 9
A	US, A, 3819249 (M. BORNER et al.) 25 June 1974 see figures 1, 2; column 1, lines 56-61; column 2, lines 5-15, 56-67; column 3, lines 1-43	1, 9, 12
A	Patent Abstracts of Japan, vol. 6, no. 88 (P-118)(966), 26 May 1982, & JP, A, 5724906 (NIPPON DENSHIN DENWA KOSHA) 9 February 1982 see the whole abstract ./.	1, 9
<div style="display: flex; justify-content: space-between;"> <div style="width: 45%;"> <p>¹⁰ Special categories of cited documents: ¹⁰</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> </div> <div style="width: 45%;"> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"A" document member of the same patent family</p> </div> </div>		
IV. CERTIFICATION		
Date of the Actual Completion of the International Search	Date of Mailing of this International Search Report	
20th July 1989	11 AUG 1989	
International Searching Authority	Signature of Authorized Officer	
EUROPEAN PATENT OFFICE	M. VAN MOL 	

III. DOCUMENTS CONSIDERED TO BE RELEVANT (CONTINUED FROM THE SECOND SHEET)		
Category *	Citation of Document, with indication, where appropriate, of the relevant passages	Relevant to Claim No
A	US, A, 4252403 (G.C. SALISBURY) 24 February 1981 see figure 3; column 2, lines 39-68	1,7,8,11
	--	
A	Patent Abstracts of Japan, vol. 5, no. 48 (P-55)(720), 7 April 1981; & JP, A, 564111 (NIPPON DENSHIN DENWA KOSHA) 17 January 1981 see the whole abstract	1,6
	--	
A	GB, A, 2128766 (STC) 2 May 1984 see the whole document	1,3
	--	
Y	10th European Conference on Optical Communication, Stuttgart, 3-6 September 1984, North-Holland (Amsterdam, NL), K. Mathyssek et al.: "New coupling arrangement between laser diode and single mode fiber with high coupling efficiency and particularly low feedback effect", pages 186-187 see the whole article	1
	--	
A		9,13,14
	--	
A	EP, A, 0224282 (N.V. PHILIPS) 3 June 1987 see figures 1a,1b,2; page 4, lines 4-37; page 5, lines 1-7 -----	1,9,13,14

**ANNEX TO THE INTERNATIONAL SEARCH REPORT
ON INTERNATIONAL PATENT APPLICATION NO.**

GB 8900455
SA 28450

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report. The members are as contained in the European Patent Office EDP file on 04/08/89. The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
DE-A- 3609407	24-09-87	None	
US-A- 3819249	25-06-74	DE-A- 2048439	06-04-72
		FR-A- 2110190	02-06-72
		GB-A- 1373543	13-11-74
		SE-B- 391585	21-02-77
US-A- 4252403	24-02-81	None	
GB-A- 2128766	02-05-84	None	
EP-A- 0224282	03-06-87	NL-A- 8502625	16-04-87
		JP-A- 62075407	07-04-87
		US-A- 4784466	15-11-88